

# Coating Portfolio



		Main Properties	Micro Hardness HV 0,025	Friction Coeff	Max Service Temp. °C	Color
<b>TiN</b>	TiN	tough & multi purpose	2300	0,5	600	gold light
	TiN HP	higher toughness & hardness	2700	0,5	750	brown
<b>TiCN</b>	TiCN G	very hard & tough	3400	0,3	450	grey
	TiCN P	hard & very tough	3100	0,3	450	pink
	MpC C-Form	hard & lubricant	3100	0,17	450	anthracite
<b>ZrN</b>	ZrN	low sticking & chemical inert	2400	0,4	600	light yellow
	ZrCN	incr. hardness, low sticking & inert	2600	0,4	600	light brown
<b>CrN</b>	CrN	tough & chemical inert	2000	0,3	0,4	metal silver
<b>AlTiN</b>	ALTiN nano	oxidation resistant & hot hardness	3200	0,5	900	violet grey
	AlTiCN	low sticking	3200	0,5	800	dark grey
	GearCut	against crater wear	3200	0,5	900	dark grey
<b>AlCrN based AlTiCrN</b>	MpC+4	shock resistant & tough	3300	0,5	1000	anthracite
	MpC+4 G	lower thermal conductivity	3300	0,5	1100	grey
<b>AlTiSiN</b>	HardMill Plus	lowest thermal conductivity, hot hardness & oxidation resistant	3800	0,5	> 1100	green
	HardMill Micro		3800	0,4	> 1100	brown
	HardDrill		3800	0,5	> 1100	dark brown
	HardGearCut		3800	0,5	> 1100	brown
<b>Nanocomposite Micro Alloyed</b>	Micral 5	thermal stable, against cold welding	3300	0,5	1100	purple
	Micral 5 micro	thermal stable, against cold welding	3300	0,5	1100	dark grey
	Micral Cast	high oxidation resistant & low thermal conductivity	3800	0,5	> 1100	dark brown
	Micral Titan Plus	very tough & heat resistant	3500	0,5	1100	blue
<b>ta-C</b>	Ta:C	high wear resistance, very low friction, chemical inert	> 5500	0,1	500	rainbow <-> grey

**PD2i Europe**  
Dirk Haack  
info@pd2i.com  
Tel +49 (0) 2421 692 3000

**PD2i France**  
Pierre Collignon  
info@pd2i.com  
Tel +33 (0) 153 75 45 05

**North America**  
Dave Schwab  
dave.schwab@pd2i.com  
Tel +1 847 668 7279

**South East Asia**  
Leong Sai Yeong  
syleong@nanogrind.com  
Tel +60 12 482 2006

**China**  
Hee Choon Tan  
heechoon.tan@pd2i.com  
Tel +86 136 0005 6796

**Taiwan**  
David Tseng  
panfolksdavid@gmail.com  
Tel +886 937 759 426

[www.PD2i.com](http://www.PD2i.com)

**Korea**  
Yeojong Yoon  
Yeojong.Yoon@pd2i.com  
Tel +821 054 576 691

